



**KUTRILIN**

## **KEDOBET PA 701**

**KEDOBET PA 701 is additive with specific composition that can meet different demands for concrete in civil engineering**

### **Description and scope**

**KEDOBET PA 701** is a concrete additive that acts as a plasticizer which allows better utilization of the effectiveness of the used cement. It reduces the need for water and provides better workability of concrete.

**KEDOBET PA 701** allows retraction of micro pores and ensures even distribution of pores in the concrete matrix, which contributes to a better resistance of concrete on cycles of freezing and thawing, and resistance to de-icing salts.

**KEDOBET PA 701** contains a retarding component which provides extended workability time of concrete and makes it suitable for production of ready mix concrete.

**KEDOBET PA 701** is particularly suitable for the concrete elements exposed to the freezing and thawing processes but can be used also for RCC because it helps the workability of concrete with low water content

### **Dosage**

In normal conditions recommended dosage is 0,4-1,3 kg per 100 kg of binder.

In special cases it can be recommended different dosage in accordance with the specific conditions on site. In such case please consult our technical department.

### **Application**

**KEDOBET PA 701** is a liquid admixture and need to be added to the concrete during the mixing process. Best results are obtained when the additive is added after all the other components already in the mixer and after the addition of at least 70% of total water. The amount of water in the mixture is adjusted to desired consistency or workability. Given the different needs for recessed air dosing is optimized according to a higher or lower amount of needed air content.

**KEDOBET PA 701** must be used at temperatures above + 5 °C and if it has been stored at low temperatures should be kept 24 h in a heated area before use and thoroughly homogenized.

**Density:** 1.13±0.030 g/cm<sup>3</sup>

**pH:** 13±1

**Appearance:** Dark brown liquid

**KEDOBET PA 701** can also be used with other KEDOBET products with prior consultation with our technical department.

### **Packing and storage**

**KEDOBET PA 701** is available in 50 kg can, 180 kg barrel, 1100 kg IBC or in bulk.



**KEDOBET PA 701** must be stored in a room where the temperature is not lower than 5 °C. In case of freezing products it is necessary to increase the product temperature to 30 °C and stir again.

The shelf life of the product is at least 2 years in original packing.

Replaces all previous releases for this product.  
November, 2019.

CONFIRMATION OF CONFORMITY	DECLARATION OF PERFORMANCE 2477-CPR-2790-008													
 2477	1. Inique identification mark of product: <b>KEDOBET PA 701</b> 2. Intended use of the construction product acc to EN 934-2: <b>Air entraining admixture</b> 3. Name, registered trade name or registered trademark and contact address of the producer: <b>KUTRILIN d.o.o., Radnička cesta 173P, HR-10000 Zagreb</b> 4. The system or systems for assessing and verifying the stability of the properties of the construction product, as set out in Annex V.CPR: <b>System 2+</b> 5. The product is in compliance with the harmonized standard: <b>EN 934-2 Admixtures for concrete, mortar and grout - Part 2: Concrete admixtures</b> <b>Name and identification number of the notified body:</b> <b>Institut IGH d.d., NB 2477</b> 6. Evaluation of characteristics in relation to standard requirements													
<b>KUTRILIN d.o.o. 10000 Zagreb</b> <b>Radnička cesta 173P</b>  <b>15</b>  <b>2477-CPR-2790-008</b>														
<b>HRN EN 934-2</b> <b>Air entraining admixture</b> <b>KEDOBET PA 701</b>														
<table border="0"> <tr> <td style="padding-right: 20px;">Chloride ion content</td> <td>≤0,1% by mass</td> </tr> <tr> <td>Alkali content</td> <td>≤6,0% by mass</td> </tr> <tr> <td>Corrosion behaviour promotion effects on steel embedded in concrete</td> <td>No corrosion</td> </tr> <tr> <td>Hazardous substances</td> <td>Do not content</td> </tr> </table>		Chloride ion content	≤0,1% by mass	Alkali content	≤6,0% by mass	Corrosion behaviour promotion effects on steel embedded in concrete	No corrosion	Hazardous substances	Do not content					
Chloride ion content		≤0,1% by mass												
Alkali content	≤6,0% by mass													
Corrosion behaviour promotion effects on steel embedded in concrete	No corrosion													
Hazardous substances	Do not content													
<table border="1"> <thead> <tr> <th>An important feature</th> <th>Property</th> </tr> </thead> <tbody> <tr> <td>Chloride ion content</td> <td>≤0,1% by mass</td> </tr> <tr> <td>Alkali content</td> <td>≤6,0% by mass</td> </tr> <tr> <td>Corrosion behaviour</td> <td>No corrosion promotion effects on steel embedded in concrete</td> </tr> <tr> <td>Compressive strength T5</td> <td>Pass</td> </tr> <tr> <td>Air content in fresh concrete (entrained air) T5</td> <td>Pass</td> </tr> <tr> <td>Air void characteristics in hardened concrete T5</td> <td>Pass</td> </tr> </tbody> </table>	An important feature	Property	Chloride ion content	≤0,1% by mass	Alkali content	≤6,0% by mass	Corrosion behaviour	No corrosion promotion effects on steel embedded in concrete	Compressive strength T5	Pass	Air content in fresh concrete (entrained air) T5	Pass	Air void characteristics in hardened concrete T5	Pass
An important feature	Property													
Chloride ion content	≤0,1% by mass													
Alkali content	≤6,0% by mass													
Corrosion behaviour	No corrosion promotion effects on steel embedded in concrete													
Compressive strength T5	Pass													
Air content in fresh concrete (entrained air) T5	Pass													
Air void characteristics in hardened concrete T5	Pass													

7. The product type described in item 1 is in compliance with the stated properties from item 6. Only the producer designated in point 3 is responsible for issuing the declaration of performance.

December, 2020.