



KUTRILIN

KEDOBET SP 101

Polycarboxylate-based superplasticizer for precast elements

Description and scope

KEDOBET SP 101 is the latest generation superplasticizer based on polycarboxyl ether polymer. The specially designed molecular structure of this product, based on years of experience and the latest research results, enables a wide field of application in modern concrete production.

The application of this superplasticizer allows for high water reductions and accelerates cement hydration. Due to the rapid adhesion of the molecules to the cement particles, combined with the effective scattering effect, the increased cement grain surface is exposed to the reaction with water.

As a result of this effect, it is possible to achieve significantly earlier development of hydration heat, rapid development of hydration products and thus increased early strength, which is especially suitable in case for early removal of the formwork.

KEDOBET SP 101 is suitable for the production of liquid consistency reoplastic concrete, without segregation, with low water-cement factor and high initial and final strength.

It is also well suited for the production of easy compacting concrete (ECC) because it can be used without the use of vibrators with a significant reduction of installation time by applying a suitable concrete mix.

KEDOBET SP 101 can be used in combination with other chemical and mineral additives to achieve specific properties as required by the project. Particularly good results in combination with fly ash. For combination with other chemical and mineral additives, please consult our technical service.

The use of **KEDOBET SP 101** is recommended at ambient temperatures above 5 ° C.

Dosage

Under normal conditions, an amount of 0.2 - 1.5 kg per 100 kg of binder is recommended.

In special cases, other quantities may be recommended according to the specific conditions at the installation site. In this case, please consult our technical service.

Application

KEDOBET SP 101 is a liquid additive intended to be added to concrete during the mixing process of ingredients. Best results are obtained when the additive is added after all other components are already in the mixer and after at least 70% of the total amount of water has been added. The amount of water required in the mixture is adjusted to the desired consistency or workability.


Packing and storage

KEDOBET SP 101 can be purchased in 25 kg bins, 150 kg barrels, 1100 kg containers or in larger quantities to order.



KEDOBET SP 101 must be stored in a place where the temperature is not lower than 5 °C. In the event of product freezing, increase the product temperature to 30 °C and mix again.

Replaces all previous releases for this product.
November, 2019.

CONFIRMATION OF CONFORMITY	DECLARATION OF PERFORMANCE 2477-CPR-2790-002																		
 2477	1. Inique identification mark of product: KEDOBET SP 101 2. Intended use of the construction product acc to EN 934-2: High range water reducing/ superplasticizing admixtures 3. Name, registered trade name or registered trademark and contact address of the producer: KUTRILIN d.o.o., Radnička cesta 173P, HR-10000 Zagreb 4. The system or systems for assessing and verifying the stability of the properties of the construction product, as set out in Annex V.CPR: System 2+ 5. The product is in compliance with the harmonized standard: EN 934-2 Admixtures for concrete, mortar and grout - Part 2: Concrete admixtures Name and identification number of the notified body: Institut IGH d.d., NB 2477 6. Evaluation of characteristics in relation to standard requirements																		
KUTRILIN d.o.o. 10000 Zagreb Radnička cesta 173P 14 2477-CPR-2790-002																			
HRN EN 934-2 High range water reducing/ superplasticizing admixture KEDOBET SP 101																			
<table border="0"> <tr> <td>Chloride ion content</td> <td style="text-align: right;">≤0,1% by mass</td> </tr> <tr> <td>Alkali content</td> <td style="text-align: right;">≤1,0% by mass</td> </tr> <tr> <td>Corrosion behaviour</td> <td style="text-align: right;">No corrosion promotion effects on steel embedded in concrete</td> </tr> <tr> <td>Hazardous substances</td> <td style="text-align: right;">Do not content</td> </tr> </table>		Chloride ion content	≤0,1% by mass	Alkali content	≤1,0% by mass	Corrosion behaviour	No corrosion promotion effects on steel embedded in concrete	Hazardous substances	Do not content										
Chloride ion content		≤0,1% by mass																	
Alkali content	≤1,0% by mass																		
Corrosion behaviour	No corrosion promotion effects on steel embedded in concrete																		
Hazardous substances	Do not content																		
	<table border="1"> <thead> <tr> <th style="text-align: center;">An imporatant feature</th> <th style="text-align: center;">Property</th> </tr> </thead> <tbody> <tr> <td>Chloride ion content</td> <td style="text-align: center;"><i>≤0,1% by mass</i></td> </tr> <tr> <td>Alkali content</td> <td style="text-align: center;"><i>≤1,0% by mass</i></td> </tr> <tr> <td>Corrosion behaviour</td> <td style="text-align: center;"><i>No corrosion promotion effects on steel embedded in concrete</i></td> </tr> <tr> <td>Compressive strenght T3.1/3.2</td> <td style="text-align: center;"><i>Pass</i></td> </tr> <tr> <td>Air content in fresh concrete T3.1/3.2</td> <td style="text-align: center;"><i>Pass</i></td> </tr> <tr> <td>Water reduction T3.1</td> <td style="text-align: center;"><i>Pass</i></td> </tr> <tr> <td>Increase in consistence T3.2</td> <td style="text-align: center;"><i>Pass</i></td> </tr> <tr> <td>Retention of consistence T3.2</td> <td style="text-align: center;"><i>Pass</i></td> </tr> </tbody> </table>	An imporatant feature	Property	Chloride ion content	<i>≤0,1% by mass</i>	Alkali content	<i>≤1,0% by mass</i>	Corrosion behaviour	<i>No corrosion promotion effects on steel embedded in concrete</i>	Compressive strenght T3.1/3.2	<i>Pass</i>	Air content in fresh concrete T3.1/3.2	<i>Pass</i>	Water reduction T3.1	<i>Pass</i>	Increase in consistence T3.2	<i>Pass</i>	Retention of consistence T3.2	<i>Pass</i>
An imporatant feature	Property																		
Chloride ion content	<i>≤0,1% by mass</i>																		
Alkali content	<i>≤1,0% by mass</i>																		
Corrosion behaviour	<i>No corrosion promotion effects on steel embedded in concrete</i>																		
Compressive strenght T3.1/3.2	<i>Pass</i>																		
Air content in fresh concrete T3.1/3.2	<i>Pass</i>																		
Water reduction T3.1	<i>Pass</i>																		
Increase in consistence T3.2	<i>Pass</i>																		
Retention of consistence T3.2	<i>Pass</i>																		

7. The product type described in item 1 is in compliance with the stated properties from item 6. Only the producer designated in point 3 is responsible for issuing the declaration of performance.

December, 2020.